

# SORA barrier 1GO 8 WS-H



SORA barrier 1GO 8 WS—H is a one—side grease and oil resistant, high wet—strength wrapping paper.

## barrier 1GO 8 WS-H

TS — 12. 11. 2020

	STANDARD	50	55	60	Tolerance
GRAMMAGE [g/m <sup>2</sup> ]	ISO 536	50	55	60	± 2
THICKNESS [μm]	ISO 534	61	67	71	± 4
SMOOT. BENDTSEN [ml/min]	DIN EN ISO 1924	200	200	200	
TENSILE STRENGTH (MD) [kN/m]	DIN EN ISO 1924	4.8	5.0	5.5	
TENSILE STRENGTH (CD) [kN/m]	ISO 2758	3.0	3.3	3.6	
BURST [kPa]	DIN 53112	200	240	280	
WET STRENGTH [%]	ISO 535	20	20	20	min
COBB <sub>10</sub> [gH <sub>2</sub> O/m <sup>2</sup> ]	ISO 2471	20	20	20	± 5
ISO BRIGHTNESS [%]	ISO 2470-2 (D65/10°)	85	85	85	
KIT TEST	T559	8	8	8	± 1
MOISTURE CONTENT [%]	ISO 287	5.5	5.5	5.5	

Given values can be used as guide values only and can be changed without prior notice.  
For a valid specification, please refer to the one most recently published on the website [www.goricane.si](http://www.goricane.si).  
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

