

# SORA barrier 2GO 5 WS-M

SORA barrier 2GO 5 WS-M is a grease and oil resistant, medium wet—strength wrapping paper.



## barrier 2GO 5 WS-M

TS — 12. 11. 2020

	STANDARD	<b>30</b>	<b>36</b>	<b>38</b>	<b>40</b>	<b>45</b>	<b>50</b>	<b>55</b>	Tolerance
GRAMMAGE [g/m <sup>2</sup> ]	ISO 536	30	36	38	40	45	50	55	± 2
THICKNESS [µm]	ISO 534	40	45	48	50	56	61	67	± 4
SMOOT. BENDTSEN [ml/min]	ISO 8791- 2	200	200	200	200	200	200	200	
TENSILE STRENGTH (MD) [kN/m]	DIN EN ISO 1924	3.0	3.3	3.5	3.8	4.5	4.8	5.0	
TENSILE STRENGTH (CD) [kN/m]	DIN EN ISO 1924	1.8	2.0	2.1	2.3	2.7	3.0	3.3	
BURST [kPa]	ISO 2758	120	140	150	160	180	200	240	
WET STRENGTH [%]	ISO 535	12	12	12	12	12	12	12	min
COBB <sub>60</sub> [gH <sub>2</sub> O/m <sup>2</sup> ]	ISO 2471	20	20	20	20	20	20	20	± 5
ISO BRIGHTNESS [%]	ISO 2470-2 (D65/10°)	85	85	85	85	85	85	85	
KIT TEST	T559	5	5	5	5	5	5	5	± 1
MOISTURE CONTENT [%]	ISO 287	5.5	5.5	5.5	5.5	5.5	5.5	5.5	

Given values can be used as guide values only and can be changed without prior notice.  
For a valid specification, please refer to the one most recently published on the website [www.goricane.si](http://www.goricane.si).  
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.



**ISEGA**

**GORIČANE**