


SORA medico opaque

SORA medico opaque is lightweight woodfree uncoated paper with high opacity.



medico opaque

TS — 20.1.2026

	STANDARD	32	35	37	40	45	50	60	Tolerance
GRAMMAGE [g/m ²]	ISO 536	32	35	37	40	45	50	60	± 2
THICKNESS [µm]	ISO 534	40	43	46	49	55	61	72	± 4
SMOOTHNESS BENDTSEN [ml/min]	ISO 8791-2	130	130	130	130	130	130	130	max
RELATIVE HUMIDITY [%]	DIN 53118	47.5	47.5	47.5	47.5	47.5	47.5	47.5	± 7.5
CIE WHITENESS [%]	ISO 2470-2 (D65/10°)	117	117	117	117	117	117	117	± 4
OPACITY [%]	ISO 2471	76	79	81	83	85	88	91	± 2

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC certified products are available in the Sales department.

