

# SORA barrier ECO

SORA barrier ECO is a fluorine-free, grease- and oil-resistant, double-sided paper with medium wet-strength.



## barrier ECO 2GO 5WS-M

TS – 29. 9. 2022

STANDARD		40	45	Tolerance
GRAMMAGE [g/m <sup>2</sup> ]	ISO 536	40	45	± 2
THICKNESS [μm]	ISO 534	50	56	
SMOOT. BENDTSEN [ml/min]	ISO 8791- 2	200	200	
WET STRENGTH [%]	ISO 12625-5	12	12	min
ISO BRIGHTNESS [%]	ISO 2470-2 (D65/10°)	84	84	
COBB 120 [CASTOR OIL] [G/M2/120 S]]	ISO 11475 (D65/10°)	1,9	1,9	max
MOISTURE CONTENT [%]	ISO 287	4,5	4,5	

Given values can be used as guide values only and can be changed without prior notice.  
For a valid specification, please refer to the one most recently published on the website [www.goricane.si](http://www.goricane.si).  
Information on the supplies of FSC® and PEFC certified products are available in the Sales department.

